

**Mapco LubeAdd 3022** is an Additive to meet API SL/SM/ SN specifications in Four Stroke Engine. It can provide better lubricity along with anti-corrosion properties to increase engine life. Added friction modifier in LubeAdd 3022 provides smooth operation at a lower treatment rate.

## **Recommended Dosages:**

| API | SAE VISCOSITY GRADE        | TREAT RATE |
|-----|----------------------------|------------|
| SL  | 20W40, 15W40, 20W50        | 5.20%      |
| SM  | 20W40, 15W40, 10W30, 20W50 | 5.80%      |
| SN  | 20W40, 15W40, 10W30        | 6.20%      |

## **Product Quality Characteristics:**

| PROPERTIES                        | <b>TEST METHOD</b> | <b>TYPICAL VALUES</b>   |
|-----------------------------------|--------------------|-------------------------|
| Appearance                        | Visual Inspection  | Dark Brown Clear Liquid |
| Magnesium Content,%wt             | ASTM D4951         | 0.90%                   |
| Calcium Content,% wt              | ASTM D4951         | 2.20%                   |
| Zinc Content,% wt                 | ASTM D4951         | 0.80%                   |
| Phosphorus % wt                   | ASTM D4951         | 0.60%                   |
| Boron % wt                        | ASTM D4951         | 0.30%                   |
| Nitrogen, % wt                    | ASTM D2868         | 0.35%                   |
| TBN, mg KOH/gm                    | ASTM D2896         | 110                     |
| Flash Point                       | ASTM D92           | Min 170                 |
| Molybdenum % wt                   | ASTM D4951         | 0.03%                   |
| Kinematic Viscosity in cst@ 100°C | ASTM D445          | 50-60                   |

**Package:** The product is packed with 200kgs drums and 50kg of carbos

## **Product Storage / Handling / Transportation / Package:**

The storage temperature should not exceed 50°c the loading/unloading and blending temperature should not exceed 60°c.

📀 Corporate Office : F-48, First Floor, Kohinoor City Mall, Kirol Road,Kurla (W), Mumbai - 400 070.

**Factory :** 39 C, Mahadev Industrial Estate, Survey No. 3, Hissa No.1, Gote Ghar, Navi Mumbai - 400 0612.